

TYPICAL PROPERTIES

CHEMICAL ANALYSIS

SiO ₂	(%)	60.9
Al ₂ O ₃	(%)	24.9
Fe ₂ O ₃	(%)	1.0
TiO ₂	(%)	1.6
K ₂ O	(%)	1.1
Na ₂ O	(%)	0.2
CaO	(%)	0.2
MgO	(%)	0.4
L.O.I.	(% at 950°C)	9.2
Carbon	(%)	1.0

PHYSICAL PROPERTIES

Water of Plasticity	(%)	32.6
Dry Shrinkage	(%)	5.4
Dry M.O.R.**	(psi)	580
pH		4.3
M.B.I.	(meq/100g)	6.9
Specific Surface Area	(sq-m/g)	19.0
Soluble SO ₄ ***	(ppm)	Medium

FIRED PROPERTIES

Total Shrinkage	(%)	
Cone 5		11.5
Cone 10		14.6
Absorption	(%)	
Cone 5		12.2
Cone 10		5.5
P.C.E		31

PARTICLE SIZE

%< 20	(microns)	93
%< 10	(microns)	86
%< 5	(microns)	73
%< 2	(microns)	58
%< 1	(microns)	46
%< 0.5	(microns)	35

Production Site

IMERYS Minerals
5450 Old State Route 22
Gleason, Tennessee 38229
United States
Tel: +1 731 648 5551
Fax: +1 731 648 5248

Commercial Office

IMERYS Minerals
100 Mansell Court East
Suite 300 Roswell
GA 30076, United States
Tel: +1 770 594 0660
Customer Service Number:
Tel: +1 800 485 2529
Fax: +1 770 645 3460

** Modulus of Rupture
Specimens:
De-aired, Extruded, 50% Ball
Clay, 50% Flint

*** Soluble So₄ (ppm):
Low: Trace to 150
Med - 150 to 450
High - Greater than 450

The data quoted are determined by the use of Imerys Standard Test Methods, copies of which will be supplied on request. Every precaution is taken in production to ensure the products conform to our published data. Since the products are based on naturally occurring materials, we reserve the right to change these data should it become necessary. Sales are in accordance with our "Conditions of Sale", copies of which will be supplied on request.